



## 2 oz Self-Adhesive Mesh

---

**Weight (After Coat):** 2 ounce per square yard +/- .15 oz/yd<sup>2</sup> (65g/m<sup>2</sup> +/-5g/m<sup>2</sup>)

**Weight (Before Coat):** 1.6 ounce per square yard +/- 0.06 oz/yd<sup>2</sup> (54g/m<sup>2</sup> +/-2g/m<sup>2</sup>)

**Adhesive:** Water Based Acrylic

**Mesh Size:** 9 x 9 picks per inch (6 x 6 picks per mm)

**Thickness:** 0.009 inches - .023 cm

**Warp:** 33 Tex x 2

**Weft:** 66 Tex

**Weave:** Leno

**Resin Content:** 25% +/-5%

**Tensile Strength:** Warp 57 lbs/in (500N/50mm)

Weft 57 lbs/in (550N/50mm)

**Alkaline Resistance:** After 28-day immersion in 5% Na(OH) solution,  
the average retention rate for tensile fracture  
strength:  $\geq 50\%$

**Coating:** Alkaline Resistant



## 4.5 oz EIFS Self-Adhesive Mesh

**Weight (After Coat):** 4.5 oz/yd<sup>2</sup> +/- 0.15 oz/yd<sup>2</sup> (152g/m<sup>2</sup> +/-5g/m<sup>2</sup>)

**Weight (Before Coat):** 3.9 oz/yd<sup>2</sup> +/- 0.06 oz/yd<sup>2</sup> (132.2g/m<sup>2</sup> +/-2g/m<sup>2</sup>)

**Adhesive:** Water Based Acrylic

**Mesh Size:** 6 x 6 picks per inch (4 x4 picks per mm)

**Thickness:** 0.0135 inches - .035 cm

**Warp:** 130 Tex x 2

**Weft:** 300 Tex

**Weave:** Leno

**Resin Content:** 18% +/-2%

**Tensile Strength:** Warp 150 lbs/in (1300N/50mm)

Weft 185 lbs/in (1600N/50mm)

**Alkaline Resistance:** After 28-day immersion in 5% Na(OH) solution, the average retention rate for tensile fracture strength:  $\geq 50\%$

**Coating:** Alkaline Resistant